



TEXAS LEHIGH CEMENT Co. LP
P.O. Box 610 Buda, Texas 78610
Sales (512) 295-6111 Customer Service (800) 252 - 5408

Plant: Buda
701 Cement Plant Road
Buda, Texas, 78610
Contact: Victor Gonzalez
Phone: (512) 295-9241
Fax: (512) 295-2431

Cement Type: V LA
Report Date: 04/12/17
Production Period: Star 03/01/17
Ends 03/31/17
Tracking No. TLCBU 0000006

**MILL TEST REPORT
AASHTO ACREDITED**

Chemical analysis % - ASTM C-114

Item	Spec. Limit	Test Results
SiO ₂ %	A	21.5
Al ₂ O ₃ %	A	4.0
Fe ₂ O ₃ %	A	4.9
MgO (%)	6.0 max.	1.2
SO ₃ (%)	2.3 max. ^E	3.0
Loss on Ignition (%)	3.5 max.	0.8
Insoluble Residue (%)	1.5 max.	0.1
CO ₂ (%)	A	0.2
Limestone (%)	5.0 max.	0.4
CaCO ₃ in Limestone (%)	70 min	80.7
Total Alkali as Na ₂ O (OPTIONAL)	0.60 max.	0.54
	Minimum	0.54
	Maximum	0.54

Inorganic processing additions & Limestone

Type		Slag	Limestone
% Addition	5% Max	0.0	0.4
SiO ₂ (%)	A	39.88	10.47
Al ₂ O ₃ (%)	A	9.37	2.86
Fe ₂ O ₃ (%)	A	5.05	0.95
CaO (%)	A	28.75	46.90
SO ₃ (%)	A	1.81	1.86

Physical Test ASTM C-150

Item		Spec. Limit	Test Result
Air content of mortar (volume %)	ASTM C-185	12 max	9
Blaine fineness (m ² /kg)	ASTM C-204	260 min.	545
Mesh 325 (45 microns) % through	ASTM C-430	A - B	99.9
Autoclave expansion (%)	ASTM C-151	0.80 max.	-0.06
Time of setting - Vicat test (minutes)			
Initial - Not less than or More than	ASTM C - 191	45 - 375	80
Final	ASTM C - 191	A	170
Compressive strength			
1 day, Minimum MPa (psi)	ASTM C-109	A - B	23.6 (3420)
3 day, Minimum MPa (psi)	ASTM C-109	8 (1160)	34.0 (4930)
7 day, Minimum MPa (psi)	ASTM C -109	15 (2180)	40.3 (5850)
28 day, Minimum MPa (psi) (OPTIONAL)	ASTM C-109	21 (3050)	51.9 (7530)
False Set (OPTIONAL)	ASTM - C451	50 min.	66
Mortar Expansion Bars	ASTM C-1038	0.020% Max ^E	in progress

Potential Compounds (%) ^C

ASTM C - 150 Annex A1	Finished cement	Base cement
C ₃ S	A 54	C ₃ S 54
C ₂ S	A 21	C ₂ S 21
C ₃ A	5 max 2	C ₃ A 2
C ₄ AF	A 15	C ₄ AF 15
(C ₄ AF + 2 x C ₃ A)	25 max 20	---- ----

A Not Applicable

B Limit not specified by purchaser. Test result provided for information only.

C Adjusted (ASTM Annex A, point A 1.6)

D Test Result of prior Month

E ASTM C-150 Table 1 Note D permits to exceed SO3 content provided it has been demonstrated to meet what is established under the Test Method ASTM C-1038 at 14 days

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of the current applicable specifications ASTM C150 and AASHTO M85. Cement analysis are reported as oxides, in accordance with ASTM Test Method C114. Silicon dioxide (SiO₂) is present in the combined state as the compounds tricalcium silicate and dicalcium silicate, and not crystalline silica. The above data represents the average of mill samples from the production stream. Inorganic processing additions have been interground in accordance with ASTM C-465. The average composition of this processing addition can be found listed above. We are not responsible for improper use or workmanship.

QC Manager: V Gonzalez-Torres