



TEXAS-LEHIGH CEMENT COMPANY



Evaluation tests for:

TLC API Class C Well Cement - Buda, Texas Plant

Typical Performance Data: Grind # 190101 Prod date: 1 - 31 January, 2019 Silo No. 7

Chemical Analysis(%) (ASTM C114)

SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	SO ₃	LOI	Na ₂ O	K ₂ O	Na ₂ O Equiv.	Insol. Residue	
21.5	4.2	4.9	62.7	1.1	2.9	1.2	0.11	0.67	0.55	0.1	
API Spec., max., %				6.0	3.5	3.0					0.75

Calculated Compounds(%) (API Spec. 10A, Table 1)

C3S	C2S	C3A	C4AF+2C3A
49	25	2.9	14.8
nr	nr	3 Max.	24 Max.

Physical Parameters

Fineness
 Blaine-m²/kg (ASTM C204) 413 API Spec.--400 min.
 -325(%) (ASTM C430) 99.2

Thickening Time and Compressive Strength(38% H₂O - neat slurry)

API Schedule	Depth ft.	Bottom Hole Circulation Temp	H ₂ O	Compressive Strength	
4-Csg	6000	113 Deg F	6.3 gal/sk	8 hr/24hr - atmos. press.	
Consistency	Thickening Time			100° F (PSI)	100° F (PSI)
Initial (Bc)	15 min. (Bc)	30 min. (Bc)	60 min. (Bc)	<u>70 Bc (min.)</u>	<u>100 Bc (min.)</u>
4	5	6	10	115	127
				912	2149

API Spec. 30 Bc max. 90 minute min. 300 PSI min. 2000 PSI min.
 in 15-30 min.
 stirring period

The cement presented meets all Spec. 10A requirements for API Class C

All well cement tests are performed according to API Spec. 10A

Calculated compounds are determined in accordance with ASTM C-114 and C-150

Victor Gonzalez-Torres

QC Manager

Phone: Lab (512) 295-9241 or (512) 295-9243, Sales (512) 295-9202, Shipping (512) 295-9222, Fax (512) 295-2431
 PO Box 610, Buda, Texas 78610 : 701 Cement Plant Road